

# Protect TL-Epoxy

## Traffic Line Epoxy



7875 Bliss Parkway North Ridgeville, OH 44039  
440-327-0015 440-353-0549 - FAX

**DESCRIPTION:**

**Protect TL-Epoxy** is a two-component, high-build, pigmented epoxy "Traffic Line" marking. **Protect TL-Epoxy** provides a permanent, high-build safety traffic line that will outwear standard paint. This product produces a very durable gloss finish.

**USES:**

Install **Protect TL-Epoxy** in industrial warehouses and manufacturing areas to designate proper safety areas and traffic patterns.

**ADVANTAGES:**

- High viscosity 100% solids pourable resin
- High build
- Excellent impact and abrasion resistance
- Hard, durable Gloss finish
- Available in standard safety colors
- Complies with VOC regulations for Industrial Maintenance Coatings in the OTC and CA.

**STORAGE:** Materials should be stored in original un-opened containers indoors between 65°F (18°C) and 90°F (32°C) and at or below 50% RH.

**SHELF LIFE:** Un-opened containers 1 year from date of manufacture.

**PACKAGING KITS/ PART NUMBERS:**

**Volume Mix Ratio: 2A: 1B**

**TLE-1003 Signal Yellow .75 gallons**

TLE-1003-A/1, TLE-B/Q

**TLE-9010 Pure White .75 gallons**

TLE-9010-A/1, TLE-B/Q

**OPTIONS**

Available in other standard and custom colors and in bulk kits.

**Protect 1000FS-B/Q** may be used to accelerate cure.

**LIMITATIONS:**

*Contamination and surface defects (fisheyes):* If contaminants of oils, silicones, mold release agents and/or others are present, **Protect TL-Epoxy** may fisheye or crawl away from the surface. Surface contaminants should be removed with a suitable detergent prior to application. Solvent cleaning of silicone contaminants is NOT recommended; please contact the lab for additional recommendations.

**MATERIAL PROPERTIES\*:**

Properties	Test Method	Results
Flash Point	ASTM D3278	≥215 °F (102°C)
Volume Solids (mixed)	ASTM D2369	100 %
Mixed Viscosity	ASTM D2196	10,000 cPs
Dry Time	ASTM D5895	Tack Free 4 hr Dry 6-10 hr Full Cure 7 days
VOC-Volatile Organic Compound	ASTM D3960	0 g/l

**CURED PROPERTIES\*:**

Properties	Test Method	Results
Abrasion Resistance Tabor CS-17, mg loss/1000 cycles/1000g mass	ASTM D4060	75 mg
Coefficient of Friction- COF James Test	ASTM D2047	0.5
Tensile Strength	ASTM D2370	8,000 psi
Adhesion to Concrete	ASTM D4541	350 psi concrete failure
Impact	ASTM D2794	20 in.lbs Direct & Reverse
Hardness (Shore D)	ASTM D2240	80
Dry Film Thickness	at 20 mils WFT	20 mils

\*Properties and results are based on laboratory testing at 72°F (22°C) %50 RH, theoretical calculations and estimates. Typical properties, as stated, are to be considered as representative of current production and should not be treated as specifications.

**RECOMMENDED APPLICATION RATE: 20 mils**

80 sq. ft. per gallon at 20 mils WFT.

2.0 sq. m, per liter at 500 microns.

One kit (.75 gallons) of mixed **Protect TL-Epoxy (pigmented)** will cover 60 sq. ft. (1.5 sq. m) at 20 mils WFT (500 microns).

One kit (.75 gallons) of mixed **Protect TL-Epoxy (pigmented)** will cover 180 lineal feet (54.9 m) at 4 inches (10cm) wide at 20 mils WFT (500 microns).

# Protect TL-Epoxy

## Traffic Line Epoxy



7875 Bliss Parkway North Ridgeville, OH 44039  
440-327-0015 440-353-0549 - FAX

### INSPECTION AND APPLICATION:

**Caution! Follow all precautions and instructions prior to installation.**

**SUBSTRATE:** The substrate must be free of curing membranes, silicate surface hardener, paint, or sealer and be structurally sound. If you suspect concrete has been treated or sealed, proceed with complete removal process. Consult your PIP representative for further instruction if silicate hardeners or membranes have been utilized.

**MOISTURE:** Moisture and moisture vapor transmission rates are dynamic in nature and may change over time. Initial testing does not guarantee future results. If the relative humidity of the concrete substrate is over 75% (using ASTM F2170), Protective Industrial Polymers must be consulted and issue a written moisture mitigation recommendation prior to product use.

**VAPOR/CONTAMINATION:** Testing for MVT does not guarantee against future problems. If there is no known vapor barrier or the vapor barrier is inadequate, there is an elevated risk of bond failure. Other factors including the migration of oils, chemicals, excessive salts or Alkali Silica Reaction (ASR) from the concrete from may also elevate the risk of adhesion difficulties. Consult your PIP representative for approved mitigation treatments.

**TEMPERATURE AND HUMIDITY:** During the application and cure of the coating, the substrate temperature, material temperature and room conditions must be maintained between 65°F (18°C) and 90°F (32°C). Relative Humidity (RH) should be limited to 30-80%. DO NOT apply coatings unless the surface temperature is more than five degree over the dew point.

### APPLICATION EQUIPMENT:

- **Protective equipment and clothing as called for in the SDS (Safety Data Sheet)**
- **Jiffy® Mixer Blade model ES.**
- **Clean container to mix materials in.**
- **Low speed high torque drill motor.**
- **High quality short nap roller covers ¼ inch mohair.**
- **Application Squeegee or application trays.**
- **Disc sanding equipment with 80-100 mesh sanding screens.**
- **Vacuum equipment.**

### PREPARATION:

Surface dirt, grease, oil and contaminates must be removed by detergent scrubbing and rinsing with clean (clear) water.

**Acid Etch (bare concrete):** {Not recommended for high build coatings} Successive acid etch treatments may be required to obtain proper adhesion to concrete. Rinse with clean water and neutralize with TSP solution.

**Shot Blasting (bare concrete):** Is a preferred method of surface preparation. Modify blaster to minimize too heavy of a surface profile and over-lap marks.

**Diamond Grind (bare concrete):** Results of grinding may vary depending on technique and the hardness of the concrete.

### APPLICATION:

**MIXING:** Premix all components at slow speed prior to mixing together. Use a Jiffy® ES mix blade attach to a slow speed drill (using a paint stick to mix is not adequate). Mix only enough

material at one time not to exceed the pot life. **Note:** Once this materials is opened and mixed it can't be resealed for later use.

**MIX:** Mix all components together for 2-3 minutes. **DO NOT THIN! APPLY Protect TL-Epoxy** at a rate of 80 sq. ft. per gallon (20 mils) to the floor surface pouring the mixed resin between two stripes of reinforced masking tape. Back roll the wet coating using a ¼ inch nap mohair roller. Remove masking tape within 20 to 30 minutes of application. This will allow the TL Epoxy to flow slightly and have a nice crisp edge.

**SPREADING RATE:** Material applied too heavy may retain air or can be soft during curing. Too little material may produce a non-uniform look.

**CURING (DRYING):** Allow the coating to cure (dry) for a minimum 24 hours after application at 75°F (24°C) and 50% RH before opening the floor to light traffic, allow more time for low temperatures and higher humidity or for heavier traffic. Full coating properties may take up to 7 days to develop.

**TECHNICAL SUPPORT:** For application questions, please contact your salesman or PIP technical service at 440-243-4560. After business hours, please contact 1-866-361-3331.

**DISPOSAL:** Dispose in accordance with federal, state, and local regulations.

**READ SDS (SAFETY DATA SHEET) FOR SAFETY AND PRECAUTIONS. USE PRODUCT AS DIRECTED FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.**

### MAINTENANCE GUIDELINES:

**Allow floor coating to cure at least one week before cleaning by mechanical means (IE: sweeper, scrubber, disc buffer).**

**CARE:** Increased life of the floor will be seen with proper maintenance and will help maintain a fresh appearance of your new Protective Industrial Polymers floor. Regularly sweep to avoid ground in dirt and grit which can quickly dull the finish, decreasing the life of the coating. Spills should be removed quickly as certain chemicals may stain and can permanently damage the finish. Only soft nylon brushes or white pads should be used on your new floor coating. Premature loss of gloss can be caused by hard abrasive bristle Polypropylene (Tynex®) brushes.

**CAUTION:** Heavy objects dragged across the surface will scratch all floor coatings. Avoid gouging or scratching the surface. Pointed items or heavy items dropped on the floor may cause chipping or concrete pop out damage.

**REPAIR:** Repair gouges, chip outs, and scratches as soon as possible to prevent moisture and chemical under cutting and permanent damage to the floor coating.

# Protect TL-Epoxy

## Traffic Line Epoxy



### WARRANTY AND CONDITIONS OF USAGE

**WARRANTY AND LIMITATION OF LIABILITY:** Protective Industrial Polymers Inc. ("PIP") warrants that its products shall conform to the manufacturer's written specifications and shall be free from defects for one (1) year from the date of purchase. PIP MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES AND DISCLAIMS THE SAME, INCLUDING, WITHOUT LIMITATION, FAILURE OF THE PRODUCT DUE TO ACTS OF GOD, FLOODING, EXTREME OR ABNORMAL TEMPERATURES, HUMIDITY AND MOISTURE, STRUCTURAL CONDITIONS, SITE PREPARATION AND CONDITIONS, ACCIDENTS, DAMAGE CAUSED BY INSTALLATION OF MACHINERY, EQUIPMENT OR FIXTURES WITHOUT ADEQUATE FLOOR PROTECTION OR WITHOUT ADEQUATE TIME FOR CURING, FAILURE TO COMPLY WITH CONDITIONS OF USAGE (SPECIFIED BELOW), VANDALISM, NEGLIGENT OR INTENTIONAL ACTS OF THIRD PARTIES OR OTHER CASUALTIES. If any PIP product fails to conform to this warranty, PIP shall either replace the product at no cost to Buyer or refund the cost of the product, in PIP's sole discretion. Replacement of any product or a refund of the cost of any product shall be the sole and exclusive remedy available to buyer, and buyer shall have no claim for incidental, special or consequential damages, including, without limitation, business interruption damages. Any warranty claim must be made within one (1) year from the date of delivery of products. PIP does not authorize anyone on its behalf to make any written or oral statements which in any way alter PIP's warranty or installation and storage information or instructions in its product literature or on its packaging labels. Any installation of PIP products which fails to conform to such installation information or instructions or the "Conditions of Usage" (specified below) shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of PIP's products for the Buyer's intended purposes.

**CONDITIONS OF USAGE:** Installation of all products purchased must be by professional installers periodically published by PIP or otherwise approved by PIP in writing. Modification to any of PIP's products voids the warranty. The installer shall maintain a written contemporaneous record of field conditions (including, without limitation, surface and atmospheric conditions, usage rates, and lot numbers of products installed). PIP reserves the right of inspection of any installed product, installation and maintenance records and records of field conditions and may conduct additional testing as is reasonably required to investigate any warranty claims. Warranty shall only apply for products or materials that have been paid for in full. Moisture Vapor Transmission (MVT) and ASR (Alkali Silica Reaction) Disclaimer and Exclusion: Although rare, some floors at or below grade level are sometimes subjected to saturation by moisture from beneath the concrete floor slab. This moisture can travel through the concrete and collect between floor toppings creating the potential for delaminating from hydrostatic pressure and/or ASR. Conditions contributing to this include heavy rainfall, broken pipes, excess hydration within fresh concrete, and other factors or defective and old concrete. These factors are difficult, if not impossible to predict. PIP recommends testing for MVT and/or the presence of ASR in the concrete substrate prior to applying any polymer floor topping. The recommended test method for MVT is ASTM F 2170-11. ASR can be predicted by a higher than normal pH within the concrete. If high pH should be detected, it is recommended a lab test for ASR. If and when delamination of the floor occurs because of a moisture condition that exists beneath or in the concrete slab beyond the capacity of the individual product installed or failure of the concrete due to ASR, this Limited Warranty does not extend to such delaminating or topping failure. This writing constitutes the sole and only agreement of warranty relating to PIP products.