

Protect 0075

Epoxy Coating System



PROTECTIVE INDUSTRIAL
POLYMERS

7875 Bliss Parkway North Ridgeville, OH 44039
440-327-0015 440-353-0549 - FAX

DESCRIPTION:

Protect 0075 is a two-component, 100% solids, epoxy coating system designed primarily for use as a clear top coat for decorative aggregate flake or quartz broadcast systems. Protect 0075 is formulated with near colorless components resulting in a very clear coating compared to standard epoxy resin coatings. Protect 0075 is extremely low yellowing and exhibits excellent blush resistance. This product can be tinted on site via the use of Protect CPU color pack which results in a solid color low yellowing epoxy finish coat.

USES:

Primary uses of Protect 0075 include intermediate, broadcast and anchor coats especially for decorative applications.

ADVANTAGES:

- Extremely low odor
- Low color
- Extremely good UV resistance
- Self Leveling
- Excellent impact and resiliency
- Tinting in field to standard and custom colors
- Complies with VOC regulations for industrial maintenance coatings in the OTC and CA*.
(*excluding SCAQMD when thinned to maximum)

STORAGE: Materials should be stored in un-opened containers between 65°F (18°C) and 90°F (32°C) and at or below 50% RH.

SHELF LIFE: 1 year from date of manufacture (un-opened).

PACKAGING KITS/ PART NUMBERS:

4 Gallon Clear Kit:

Protect 0075-A/55F (Filled to 3 gallons)
Protect 0075-B/1

20 Gallon Clear Kit:

Protect 0075-A/5 (3 ea.)
Protect 0075-B-B/5

212 Gallon Clear Kit:

Protect 0075-A/55 (3 ea.) (Filled to 53 gallons)
Protect 0075-B/55 (Filled to 53 gallons)

OPTIONS:

On Site Tinting via Protect CPU Color packs.-Protect 0075 may be tinted on site via the addition of Protect CPU color packs. Depending on color, applied thickness and opacity requirements 1 pint to 1 quart of colorant per 4 gallon mix of Protect 0075 can be used. As a general rule, white or very pastel colors applied at thicknesses less than 15 mils require the higher quart loading.

Various aggregates of different size shapes and composition can be incorporated into **Protect 0075** to improve traction in slip hazard areas.

LIMITATIONS:

Contamination and surface defects: If contaminants including oil, silicone, mold release agents and/or other materials are present, resin systems may fisheye or crawl away from the surface. All surface contaminants should be removed with a suitable detergent prior to application. Solvent cleaning of silicone based contaminants is NOT RECOMMENDED. Please contact Technical Service for additional recommendations.

MATERIAL PROPERTIES*:

Properties		Results
Flash Point	ASTM D3278	≥215 °F (102°C)
Volume Solids (mixed)	ASTM D2369	100 %
Mixed Viscosity	ASTM D2196	750-1000 cPs
Dry Time	ASTM D5895	Tack Free 12 hr Foot Traffic 18 hr Vehicular 24 hours
VOC-Volatile Organic Compound	ASTM D3960	0 g/l clear & pigmented ≤250 g/l with max thinning

CURED PROPERTIES*:

Properties	Test Method	Results
Abrasion Resistance Tabor CS-17, mg loss/1000 cycles/1000g mass	ASTM D4060	100 mg
Coefficient of Friction-COF James Test	ASTM D2047	0.55 0.65(w/NS-36)
Tensile Strength	ASTM D2370	7200 psi
Adhesion to Concrete	ASTM D4541	350 psi concrete failure
Impact	ASTM D2794	160 in.lbs
Tensile Elongation	ASTM D2370	5%
Hardness (Ultimate)	ASTM D2240	85

*Properties and results are based on laboratory testing at 72°F (22°C) %50 RH, theoretical calculations and estimates. Typical properties, as stated, are to be considered as representative of current production and should not be treated as specifications.

Protect 0075

Epoxy Coating System



7875 Bliss Parkway North Ridgeville, OH 44039
440-327-0015 440-353-0549 - FAX

CHEMICAL RESISTANCE*: Consult Protective Industrial Polymers for specific requirements.

RECOMMENDED APPLICATION RATE:
10-15 mils as an intermediate/topcoat.

INSPECTION AND APPLICATION:

Caution! Follow all precautions and instructions prior to installation.

SUBSTRATE: The substrate must be free of curing membranes, silicate surface hardener, paint, or sealer and be structurally sound. If you suspect concrete has been treated or sealed, proceed with complete removal process. Consult your PIP representative for further instruction if silicate hardeners or membranes have been utilized.

MOISTURE: Moisture and moisture vapor transmission rates are dynamic in nature and may change over time. Initial testing does not guarantee future results. If the relative humidity of the concrete substrate is over 75% (using ASTM F2170), Protective Industrial Polymers must be consulted and issue a written moisture mitigation recommendation prior to product use.

VAPOR/CONTAMINATION: Testing for MVT does not guarantee against future problems. If there is no known vapor barrier or the vapor barrier is inadequate, there is an elevated risk of bond failure. Other factors including the migration of oils, chemicals, excessive salts or Alkali Silica Reaction (ASR) from the concrete from may also elevate the risk of adhesion difficulties. Consult your PIP representative for approved mitigation treatments.

TEMPERATURE AND HUMIDITY: During the application and cure of the coating, the substrate temperature, material temperature and room conditions must be maintained between 65°F (18°C) and 90°F (32°C). Relative Humidity (RH) should be limited to 30-80%. DO NOT apply coatings unless the surface temperature is more than five degree over the dew point.

APPLICATION EQUIPMENT:

- Protective equipment and clothing as called for in the SDS (Safety Data Sheet)
- Jiffy® Mixer Blade model ES
- Clean container for mixing material
- Low speed high torque drill motor
- High quality short nap roller covers- ¼-3/8 inch nap
- Application Squeegee

PREPARATION:

Surface dirt, grease, oil and contaminants must be removed by detergent scrubbing and rinsing with clean (clear) water.

Mechanical Preparation: Shot Blasting or grinding the surface is the preferred method of preparation. The success of industrial diamond grinding as a concrete preparation method will vary depending on technique and the hardness of the concrete.

JOINTS: All non moving joints (control joints) can be filled with a rigid or semi-rigid joint compound. Construction joints may be filled with semi-rigid joint filler and might need to be re-built and re-cut depending on conditions. Isolation or expansion joints must be

filled with a flexible material designed for expansion and should not be coated over.

MIXING: Mix ratio for Protect 0075 is 3 Parts A resin to 1 part B by volume. The addition of color pack should be added and mixed in homogenously prior to adding the Part B (activator). Mix all components together for 2-3 minutes with a Jiffy® ES mix blade attached to a slow speed drill. Mix only enough material at one time that can be applied without exceeding the pot life. **Note:** Once this material is mixed, it can't be resealed for later use.

APPLICATION:

Protect 0075 is not specifically designed for application to concrete. Consult Protective Industrial Polymers for the most suitable primer for the intended application.

APPLY Protect 0075 to the floor surface using a notched or flat squeegee depending on desired thickness. Leaving the material sit in the pail longer than 5 minutes will result in an increase of heat and viscosity and reduce leveling properties. Best Practice is to empty onto floor as soon as possible to extend working time. Back roll and evenly spread the wet coating using a ¼-3/16" inch nap non-shed roller. Care should be taken to overlap and cross lap, but not over roll the coating introducing air to the surface.

RECOAT: Protect 0075 can be top coated with other PIP urethanes or epoxies within 24 hours at 70-75F 30% RH without sanding or may be used as a topcoat over existing (sound) PIP epoxy coatings. If the re-coat window has expired, the prior cured coating surface must be sanded with 100 grit sand paper or sanding screen installed on a swing-type floor buffer. Sand to a uniform dulled surface. Remove all sanding debris with a vacuum and damp mop. Scrub with detergent and rinse with clean water. Surface must be dry before coating.

SPREADING RATE: Typical spread rate for Protect 0075 is 80-100SF/gal when used as an intermediate or topcoat. Be sure to plan accordingly as there may be a need for extra material to provide proper coverage. The best practice is to measure and grid the floor to be sure of proper application rate.

CURING (DRYING): Allow the coating to cure (dry) for a minimum 24 hours after application at 75°F (24°C) and 50% RH before opening the floor to light traffic, allow more time for low temperatures and higher humidity or for heavier traffic. Full coating properties may take up to 7 days to develop.

TECHNICAL SUPPORT: For application questions, please contact your salesman or PIP technical service at 440-327-0015.

DISPOSAL: Dispose in accordance with federal, state, and local regulations.

READ SDS (SAFETY DATA SHEET) FOR SAFETY AND PRECAUTIONS. USE PRODUCT AS DIRECTED FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.

MAINTENANCE GUIDELINES:

Allow floor coating to cure at least one week before cleaning by mechanical means (IE: sweeper, scrubber, disc buffer).

Protect 0075

Epoxy Coating System

Issue/Rev Date: 9-11-2019



CARE: Increased life of the floor will be seen with proper maintenance and will help maintain a fresh appearance of your new Protective Industrial Polymers floor. Regularly sweep to avoid ground in dirt and grit which can quickly dull the finish, decreasing the life of the coating. Spills should be removed quickly as certain chemicals may stain and can permanently damage the finish.

Only soft nylon brushes or white pads should be used on your new floor coating. Premature loss of gloss can be caused by hard abrasive bristle Polypropylene (Tynex®) brushes.

CAUTION: Heavy objects dragged across the surface will scratch all floor coatings. Avoid gouging or scratching the surface.

Pointed items or heavy items dropped on the floor may cause chipping or concrete pop out damage. Plasticizer migration from rubber tires can permanently stain the floor coating. If a rubber tire is planned to set on the floor for a long period of time, place a piece of acrylic sheet between the tire and the floor to prevent tire staining. Rubber burns from quick stops and starts from lift trucks can heat the coating to its softening point causing permanent damage and marking.

REPAIR: Repair gouges, chip outs, and scratches as soon as possible to prevent moisture and chemical under cutting and permanent damage to the floor coating.

presence of ASR in the concrete substrate prior to applying any polymer floor topping. The recommended test method for MVT is ASTM F 2170-11. ASR can be predicted by a higher than normal pH within the concrete. If high pH should be detected, it is recommended a lab test for ASR. If and when delamination of the floor occurs because of a moisture condition that exists beneath or in the concrete slab beyond the capacity of the individual product installed or failure of the concrete due to ASR, this Limited Warranty does not extend to such delaminating or topping failure. This writing constitutes the sole and only agreement of warranty relating to PIP products.

WARRANTY AND CONDITIONS OF USAGE

WARRANTY AND LIMITATION OF LIABILITY: Protective Industrial Polymers Inc. ("PIP") warrants that its products shall conform to the manufacturer's written specifications and shall be free from defects for one (1) year from the date of purchase. PIP MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES AND DISCLAIMS THE SAME, INCLUDING, WITHOUT LIMITATION, FAILURE OF THE PRODUCT DUE TO ACTS OF GOD, FLOODING, EXTREME OR ABNORMAL TEMPERATURES, HUMIDITY AND MOISTURE, STRUCTURAL CONDITIONS, SITE PREPARATION AND CONDITIONS, ACCIDENTS, DAMAGE CAUSED BY INSTALLATION OF MACHINERY, EQUIPMENT OR FIXTURES WITHOUT ADEQUATE FLOOR PROTECTION OR WITHOUT ADEQUATE TIME FOR CURING, FAILURE TO COMPLY WITH CONDITIONS OF USAGE (SPECIFIED BELOW), VANDALISM, NEGLIGENT OR INTENTIONAL ACTS OF THIRD PARTIES OR OTHER CASUALTIES. If any PIP product fails to conform to this warranty, PIP shall either replace the product at no cost to Buyer or refund the cost of the product, in PIP's sole discretion. Replacement of any product or a refund of the cost of any product shall be the sole and exclusive remedy available to buyer, and buyer shall have no claim for incidental, special or consequential damages, including, without limitation, business interruption damages. Any warranty claim must be made within one (1) year from the date of delivery of products. PIP does not authorize anyone on its behalf to make any written or oral statements which in any way alter PIP's warranty or installation and storage information or instructions in its product literature or on its packaging labels. Any installation of PIP products which fails to conform to such installation information or instructions or the "Conditions of Usage" (specified below) shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of PIP's products for the Buyer's intended purposes.

CONDITIONS OF USAGE: Installation of all products purchased must be by professional installers periodically published by PIP or otherwise approved by PIP in writing. Modification to any of PIP's products voids the warranty. The installer shall maintain a written contemporaneous record of field conditions (including, without limitation, surface and atmospheric conditions, usage rates, and lot numbers of products installed). PIP reserves the right of inspection of any installed product, installation and maintenance records and records of field conditions and may conduct additional testing as is reasonably required to investigate any warranty claims. Warranty shall only apply for products or materials that have been paid for in full. Moisture Vapor Transmission (MVT) and ASR (Alkali Silica Reaction) Disclaimer and Exclusion: Although rare, some floors at or below grade level are sometimes subjected to saturation by moisture from beneath the concrete floor slab. This moisture can travel through the concrete and collect between floor toppings creating the potential for delaminating from hydrostatic pressure and or ASR. Conditions contributing to this include heavy rainfall, broken pipes, excess hydration within fresh concrete, and other factors or defective and old concrete. These factors are difficult, if not impossible to predict. PIP recommends testing for MVT and/or the